

Rec'd PCT/PTO 28 APR 2005

PC U03/01409




REC'D 17 NOV 2003

WIPO PCT

Patent Office  
Canberra

I, JANENE PEISKER, TEAM LEADER EXAMINATION SUPPORT AND SALES hereby certify that annexed is a true copy of the Provisional specification in connection with Application No. 2002952446 for a patent by UCC ENERGY PTY LIMITED as filed on 01 November 2002.



WITNESS my hand this  
Tenth day of November 2003

A handwritten signature in cursive script, appearing to read 'J. Peisker'.

JANENE PEISKER  
TEAM LEADER EXAMINATION  
SUPPORT AND SALES

**PRIORITY  
DOCUMENT**

SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

**AUSTRALIA**

**Patents Act 1990**

**PROVISIONAL SPECIFICATION**

**Invention Title:** .. **Process for demineralising coal**

**The invention is described in the following statement:**

## Provisional specification

### Process for demineralising coal

#### Field of the invention

The present invention relates to a process for demineralizing coal.

#### 5 Background of the invention

Several methods have been described in the literature for producing demineralized or low-ash coal for fuel and other industrial applications, but none have achieved sustained commercial use.

10 A process was developed in Germany during the 1940's for removing ash-forming mineral matter from physically cleaned black coal concentrates, involving heating the coal as a paste with aqueous alkali solution, followed by solid/liquid separation, acid washing and water washing steps. Reports on this process detail a practical chemical demineralizing method. German practice showed that a demineralized coal with an ash yield of 0.28% could be produced from a physically cleaned feed coal which had an  
15 initial ash yield of 0.8%.

The coal-alkali feed paste was stirred at 40° - 50°C for 30 minutes, then pumped through a heat exchanger to a continuously operable gas-heated tubular reactor in which the paste was exposed to a temperature of 250°C for 20 minutes, under a pressure of 100-200 atmospheres (10-20MPa). The reaction mixture was then passed through the heat  
20 exchanger previously mentioned, in order to transfer heat to the incoming feed, then cooled further in a water-cooled heat exchanger.

The cooled paste was diluted with softened water, then centrifuged to separate and recover the alkaline solution and the alkalized coal. The latter was dispersed to 5% hydrochloric acid, then centrifuged to recover the acidified coal and spent acid and  
25 redispersed in water. The coal was filtered from this slurry, dispersed again in another lot of water and centrifuged to recover the resulting low-ash coal as a damp solid product.

American and Indian researchers used broadly similar chemical methods, with variations in processing details, to produce low-ash coals from other feed coals, most of

which had much higher starting ash levels than the coals than the Germans used. Another American group (at Battelle) claimed advantages for:

- (a) Mixed alkali leachants containing cations from at least one element from Group IA and at least one element from Group IIA of the Periodic Table;
- 5 (b) Filtration or centrifugation of the alkalized coal from the spent alkaline leachant, either at the reaction temperature or after rapid cooling to less than 100°C, in order to minimise the formation of undesired constituents, presumably sodalite or similar compounds;
- (c) Application of the process to low-rank coals which dissolve in the alkali and which can be reprecipitated at a different pH from the mineral matter, thus allowing separation and selective recovery.

10

15

20

Other researchers had studied scientific aspects of alkaline extraction of sulphur and minerals, including the relative merits of different alkalis. Most American work has been directed at the removal of sulphur rather than metallic elements, and the acid treatment step is often omitted. However, an American group (at Alcoa) has chemically cleaned coal to less than 0.1% ash yield, concurrently achieving large reductions and low final concentrations of iron, silicon, aluminium, titanium, sodium and calcium. The aim was to produce very pure coal suitable for conversion into electrode carbon for the aluminium industry. This was achieved by leaching powdered coal with hot aqueous alkaline solution under pressure (up to 300°C), then successively with aqueous sulphuric acid and aqueous nitric acid at 70°-95°C.

Australian patent no. 592640 (and corresponding US patent no. 4,936,045) describes a process for the preparation of demineralized coal. This process includes the following steps:

25

- (a) forming a slurry of coal particles, preferably at least 50% by weight of which particles have a maximum dimension of at least 0.5mm, with an aqueous solution of an alkali, which solution has an alkali content of from 5 to 30% by weight, such that the slurry has an alkali solution to coal ratio on a weight basis of at least 1:1;

- (b) maintaining the slurry at a temperature of from 150° to 300°C, preferably 170°C to 230°C, for a period of from 2 to 20 minutes substantially under autogenous hydrothermal pressure and rapidly cooling the slurry to a temperature of less than 100°C;
- (c) separating the slurry into alkalized coal and a spent alkali leachant solution;
- (d) regenerating the alkali leachant solution for reuse in step (a) above by the addition of calcium or magnesium oxide or hydroxide thereto to precipitate minerals therefrom;
- (e) acidifying the alkalized coal by treatment with an aqueous solution of sulphuric or sulphurous acid to yield a slurry having a pH of from 0.5 to 1.5 and a conductivity of from 10,000 to 100,000  $\mu$ S;
- (f) separating the slurry into acidified coal and a spent acid leachant solution; and
- (g) washing the acidified coal.

Although the process described in Australian patent no. 592640 can produce a demineralized coal product having an ash content of less than 1% by weight and as low as 0.50% by weight, significant opportunities arise if the ash content can be reduced to even lower levels. If the ash level can be reduced to levels even lower than that achieved in Australian patent no. 592640, the demineralized coal product may be used as a fuel directly fired into a gas turbine. In this use, the demineralized coal could replace natural gas as a fuel for the gas turbine. Such demineralized coal could also be used as an alternative to heavy fuel oils and as a high purity carbon source for the production of metallurgical recarbonisers, carbon electrodes for aluminium production and alternative reductants for high purity silicon manufacture. The contents of US patent no. 4,936,045 are herein incorporated by cross-reference.

### Summary of the invention

In a first aspect, the present invention provides a process for demineralizing coal comprising:

- (a) forming a slurry of coal particles in an alkali solution, said slurry containing 10-30% by weight coal;
- (b) maintaining the slurry at a temperature of 220-250°C under a pressure sufficient to prevent boiling;
- (c) separating the slurry into an alkalized coal and a spent alkali leachant;
- (d) forming an acidified slurry of the alkalized coal, said acidified slurry having a pH of 0.5-1.5;
- (e) separating the acidified slurry into a coal-containing fraction and a substantially liquid fraction;
- (f) subjecting the coal-containing fraction to a hydrothermal washing step in which the coal-containing fraction is mixed with water and a polar organic solvent or water and an organic acid to form a mixture; and
- (g) separating the coal from the mixture in step (f).

The coal that is provided to step (a) is suitably a medium to high rank coal, most suitably a bituminous coal.

The coal that is provided to step (a) preferably has a total mineral content generally in the range of 2-15% by weight. More preferably, the mineral content of the coal should be as low as possible. It has been found that the chemical consumption and hence the processing cost is lower for coals of low ash content fed to step (a) of the process. Coals that are especially suitable for treatment in accordance with the process of the present invention have mineral contents that are richer in Si-based minerals and poorer in Al-based minerals.

It is preferred that the coal that is provided to step (a) of the process of the present invention is sized such that 100% is less than 1mm, more preferably 100% less than 0.5mm. The coal also preferably contains a minimum of material less than 20 microns.

more preferably less than 5% by weight smaller than 20microns. It has been found that excess amounts of fine material, e.g., less than 20-microns, can cause difficulties in the solid/liquid separation steps used in the present invention.

Steps (a) and (b) of the present process subject the coal to an alkali (or caustic) digestion. This results in the silicate minerals being solubilized and the clay minerals being converted to acid soluble minerals.

The slurry formed in step (a) has a coal concentration of from 10% to 30% by weight. Preferably, the coal concentration is about 25% by weight.

The alkali concentration in the liquid phase of the slurry is preferably in the range of 8% to 20% by weight, more preferably 13% to 15% by weight (calculated as NaOH equivalent). The alkali material is preferably NaOH, although other alkali materials could also be used, either singly or as a mixture of two or more alkali materials. The slurry is heated to a temperature of from 220-250°C. The slurry is preferably maintained at this temperature for a period of from 15 to 60 minutes, more preferably for about 20 minutes.

It has been found that the rate of heating the slurry should preferably be maintained at a rate of less than 2°C per minute in the temperature range of 150°C to 250°C.

It is preferred in steps (a) and (b) that the caustic slurry is formed and then heated to the desired temperature.

The slurry in step (b) is suitably maintained at the autogenous pressure of the heated slurry to prevent the slurry from boiling.

It is also preferred that the slurry be subject to agitation, especially mild agitation, in step (b). The degree of agitation is preferably such that deposition of sodalite ( $\text{Na}_4\text{Si}_3\text{Al}_3\text{O}_{12}(\text{OH})$ ) on the process vessel walls is minimised or avoided. Agitation may be achieved by any suitable agitation means known to the person of skill in the art.

Step (c) of the process of the present invention separates the caustic slurry from step (b) into an alkalized coal and a spent alkali leachant. This separation step preferably takes place at a temperature of from 50°C to 80°C. It is especially preferred that the slurry

from step (b) is cooled at a cooling rate of less than 5°C/minute more preferably less than 2°C/minute, whilst the temperature of the slurry is in the range of 240°C - 150°C.

Step (c) may suitably comprise a filtration step. As mentioned above, the filtration step preferably is conducted at a temperature of from 50°C to 80°C.

5 The spent caustic/leachant from step (c) is preferably treated to regenerate caustic and recover minerals. For example, the spent leachant may be mixed with sufficient calcium oxide or calcium hydroxide to precipitate the soluble silicate and aluminate ions as their insoluble calcium salts, while simultaneously forming soluble sodium hydroxide, thus regenerating the alkaline leachant for recycling. This procedure minimises the  
10 amount of acid needed in the next processing step and hence lowers the total costs of demineralising the coal. Instead of calcium oxide or hydroxide, the corresponding magnesium salts may be used, or the mixed oxides or hydroxides of calcium and magnesium derived from dolomite may be used.

The alkalized coal recovered from step (c) is preferably washed to remove excess  
15 alkali. The coal is preferably washed with a minimum of 3 parts by weight of water for each part by weight of dry coal, more preferably 5 parts by weight water for each part by weight of dry coal.

The alkalized coal from step (c) may also be treated to remove sodalite therefrom prior to sending to the acid soak step. The sodalite may be separated from the alkalized  
20 coal by physical methods such as selective screening, heavy media float-sink methods, or froth flotation. The sodalite may provide a valuable by-product whilst reducing the amount of acid required in step (d).

Step (d) of the process of the present invention may suitably involve mixing the coal from step (c), more preferably washed coal from step (c), with water or an acid  
25 solution to obtain a slurry. The slurry preferably has a coal concentration that falls within the range of 5% to 20% by weight, more preferably about 10% by weight. If the slurry is formed by mixing with water, it may be suitably acidified by mixing it with an acid.

Step (d) preferably forms a slurry that contains a mineral acid, more preferably sulphuric acid or hydrochloric acid.



The acidified slurry has a pH that falls in the range of 0.5 to 1.5, more preferably pH about 1.0.

The temperature of the slurry in step (d) preferably falls within the range from 20°C to 90°C, more preferably from 30°C to 60°C.

5 The slurry may be suitably agitated in the acid solution.

The coal is preferably maintained in contact with the acid solution in step (d) for a period of at least 20 minutes, more preferably about 60 minutes.

10 In one embodiment of the present invention, the coal in the slurry of step (d) is separated after an appropriate time in step (e) and passed to step (f). In a more preferred embodiment, the coal fraction from step (e) is re-slurried with water and acid and brought to a pH of between 0.5 and 1.5, more preferably pH 1.0, for a further period of time of greater than 20 minutes, more preferably about 60 minutes.

The step of re-slurrying the coal may be repeated between one and four times. Fresh acid solution may be used for the re-slurrying.

15 Alternatively, the re-slurrying may comprise a countercurrent mixing stage.

20 Step (e) involves separating the acidified slurry into a coal-containing fraction and a liquid fraction. This may be achieved using any suitable solids/liquid separation means known to the skilled person. Filtration is preferred. If the filtercake is to be re-slurried with acid, it does not require washing. After the final stage of acid re-slurrying, the filtercake may be given a minimal water wash such that when the filtercake is re-slurried in fresh water, the pH of the solution is preferably about 2.

The spent acid may be treated to regenerate an alkali solution and to obtain the controlled precipitation of minerals as by-products. For example, the spent acid may be treated with calcium oxide to regenerate a caustic solution and precipitate the minerals.

25 The hydrothermal wash step involves two possible options. One of these is to mix the coal from the last of the acid soak steps with a solution of water and a polar organic solvent. The polar organic solvent is suitably miscible with water. The polar organic solvent is preferably an alcohol, more preferably ethanol.

The coal is preferably mixed with the solution of water and polar organic solvent such that a slurry having a solids content of 10-30% by weight, more preferably about 25% by weight. The residual acidity from the acid-soak step(s) is preferably such that the pH of the slurry is from 1.5 to 2.5, and more preferably about 2.0.

5 The slurry is preferably heated to a temperature of from 240°C to 280°C, more preferably 260°C to 270°C, in step (f). The slurry is preferably kept at temperature for a period of between 1 minute and 60 minutes, more preferably about 5 minutes.

The slurry of coal/water/polar organic solvent is preferably heated at a heating rate of between 2°C per minute and 20°C per minute.

10 The pressure of the slurry is such that boiling is prevented. The slurry is preferably heated under autogenous pressure. At the preferred temperature specified above, the autogenous pressure is approximately 8 MPa.

As mentioned above, the presently preferred polar organic solvent is ethanol. It is especially preferred that the liquid phase mixed with the coal to produce the slurry is a 15 50% ethanol in water solution

Option 1 of the hydrothermal washing stage reduces the level of the Na, Si, Fe and Ti, but it is primarily active in reducing Na and Si. If only Na is required to be reduced, the temperature used in the hydrothermal wash stage can be as low as 10°C, with operation at ambient temperature being especially suitable.

20 The second option for the hydrothermal washing stage involves mixing the coal from the acid-soak step(s) with an aqueous solution of an organic acid. Citric acid is presently the preferred organic acid.

The citric acid solution preferably contains between 5% and 20% by weight citric acid (hydrated basis), more preferably about 10% by weight. The coal concentration in 25 the slurry is preferably in the range of 10% to 30% by weight, more preferably about 25% by weight. The slurry is preferably heated to a temperature of between 240°C to 280°C, more preferably between 250°C to 270°C. The pressure should be maintained at a level sufficient to prevent boiling. The pressure is suitably the autogenous pressure which, for the temperature range specified above, is approximately 8 MPa. The slurry is preferably

kept at the elevated temperature for a period of between 1 minutes and 60 minutes, more preferably about 5 minutes. The slurry is preferably heated to the elevated temperature at a heating rate of between 2°C per minute and 20°C per minute.

In another embodiment of the second option, the slurry may be heated to a temperature of between 150°C and 160°C. In this embodiment, Na and Fe will not be removed.

Without wishing to be bound by theory, the present inventors have postulated that two mechanisms may be taking place in the hydrothermal washing step to further reduce the ash content, these being:

(i) the residual acid in the coal from the acid soak step(s) results in the slurry of step (d) being acidified, eg. to a pH of between 1.5 and 2.5. This promotes further mineral dissolution;

(ii) it is thought that humic compounds are formed by interaction between the coal and the alkali in steps (a) and (b). In the acid soak step(s), these humic compounds "collapse" and tie up some of the Na. In the hydrothermal washing step, option 1, the alcohol allows the humics to hydrolyse to release the Na. The Na reports to the water phase following alcohol/water separation. The alcohol can be recycled, essentially in a closed loop recycling step, thus minimising alcohol consumption. In option 2, the citric acid facilitates release of the Na from the humics.

Step (g) of the process of the present invention involves separating the coal from the mixture or slurry in step (f). This solid/liquid separation may be achieved by any means known to be suitable by a person of skill in the art. Filtration is preferred.

It is preferred that the coal recovered from step (g) be washed. Preferably the washing uses a minimum of one part of clean water for each part of coal, by weight.

The process in accordance with the first aspect of the present invention can produce a demineralised coal product having an ash content of from 0.01-0.2%, by weight. The process also removes Na from the coal and thus it is believed that the ash fusion temperature of the ash remaining in the coal is also advantageously increased by the process. The ash fusion temperature is important if the demineralised coal is to be

used as a fuel for gas turbines as these require that the ash fusion temperature be greater than 1350°C; more preferably greater than 1500°C.

The process of the first aspect of the present invention is capable of achieving demineralised coal having an ash content of less than 0.2% by weight preferably from 0.01% to 0.2% by weight, with trials involving some coals achieving an ash content of 0.01% by weight. Steps (a) to (e) of this process of the first aspect of the invention are capable of producing a demineralised coal having an ash content as low as 0.3-0.4% by weight. For some uses, this ash content is acceptable and the further processing of the hydrothermal washing step may not be necessary.

Accordingly, in a second aspect, the present invention provides a process for demineralising coal comprising steps (a) to (e) of the process described with reference to the first aspect of the present invention.

The hydrothermal washing stage has also been shown to reduce the ash content of the coal. This also suggests that the hydrothermal washing stage can be used as a stage in a demineralisation process that includes steps other than steps (a) to (e) as described with reference to the first aspect of the present invention.

Accordingly, in a third aspect, the present invention provides a process for demineralising coal comprising the steps of alkali digestion followed by acid soaking and wherein coal from the acid soaking step is subjected to a further step as described with reference to step (f) of the first aspect of the present invention.

The demineralised coal is preferably subjected to a binderless briquetting process to form a final product of enhanced handleability.

### Brief description of the drawings

Figure 1 is a process flowsheet of an embodiment of a process for demineralising coal in accordance with the first aspect of the invention;

Figure 2 is a process flowsheet of one embodiment of the acid soak step of Figure

1;

Figure 3 is a process flowsheet of an alternative embodiment of the acid soak step of Figure 1;

Figure 4 is a process flowsheet of an embodiment of a process for demineralising coal in accordance with the second aspect of the invention; and

Figure 5 is a process flowsheet of an embodiment of a process for demineralising coal in accordance with the third aspect of the invention.

### Detailed description of the drawings

In considering the drawings, it will be appreciated that the drawings are provided for the purposes of illustrating preferred embodiments of the invention. Therefore, the invention should not be considered to be limited to the features shown and described with reference to the drawings.

A flow-sheet for a demineralisation process in accordance with the present invention is shown in figure 1. In figure 1, a slurry 11 of coal and caustic solution is fed to a caustic digestion vessel 10. Caustic digestion vessel 10 is suitably an autoclave or a pressure vessel that allows the slurry of caustic solution and coal to be heated.

The caustic solution 12 that is fed to caustic digestion vessel 10 comprises a sodium hydroxide solution having a sodium hydroxide concentration of 13 to 15%. The coal 11 and sodium hydroxide solution 12 are fed to caustic digestion vessel 10 in amounts such that a slurry containing 25% coal is achieved. The caustic digestion vessel 10 is stirred using a suitable agitator to assist in minimising or preventing the deposition of sodalite on the walls of the vessel.

The slurry of coal and caustic solution in vessel 10 is heated to a temperature of from 220 to 250° Celsius. The slurry is maintained at this temperature for a period from 15 minutes to 60 minutes, with 20 minutes being especially suitable. The slurry is maintained under autogenous pressure so that the solution does not boil.

The slurry of caustic solution and coal is heated such that the rate of increase of temperature does not exceed 2° Celsius per minute when the temperature of the coal falls within the temperature range of 150 to 240° Celsius.

After the required residence time has passed, the slurry is cooled at a cooling rate of less than 5° Celsius per minute, even more suitably less than 2° Celsius per minute, whilst the temperature is in the range of 240 to 150° Celsius. The slurry is removed from caustic digestion vessel 10 and passes via line 15 into filtration unit 20. Filtration unit 20 may be any suitable filtration unit that can achieve separation of coal from the caustic solution. Belt filters and drum filters are especially useful. It will also be appreciated that other solid/liquid separation devices may be used in place of filtration unit 20. For example, thickeners or decanters may be used.

The spent caustic solution 22 recovered from filtration unit 20 is sent to caustic recovery 24. In caustic recovery 24, the spent caustic solution is regenerated. For example, the spent caustic solution may be contacted with calcium oxide, calcium hydroxide, magnesium oxide or magnesium hydroxide to precipitate minerals therefrom and regenerate sodium hydroxide. The regenerated sodium hydroxide can be reused.

The alkalisied coal 26 is then washed with water in water wash vessel 30. Water wash vessel 30 may be any suitable vessel for mixing liquids and solids. Alternatively, and preferably, water wash 30 is effected by washing the filter cake on the filtration unit 20. In this regard, if a belt filter is used, a filter cake comprising alkalisied coal and residual caustic solution is formed on the filter belt. This filter cake may be sprayed with wash water 32. As the filter cake is still in contact with the filtration unit, the wash water is removed as removed wash water 34. The wash water 34 may also be sent to caustic regeneration 24.

The washed filter cake, comprising washed alkalisied coal 36 is then fed to the acid soak process 40. In the acid soak process 40, alkalisied coal from filtration unit 20 and water wash 30 is mixed with water to give a slurry concentration in the range of 5 to 25% by weight coal, preferably 10% by weight coal. The slurry is acidified with acid 42, preferably sulfuric acid, to obtain a pH in the range of from 0.5 to 1.5, preferably pH 1.0. The temperature of the acid slurry is maintained in the range of 20° to 90°, more suitably in the range of 30° to 60° Celsius, for a period of greater than 20 minutes. It has been found that 60 minutes is a suitable time for maintaining the coal in contact with the acid.

solution. The coal should be agitated to promote mixing of the coal with the acid solution.

The acid wash soak process 40 may comprise a single contact between the acid solution and the coal. However, it is preferred that the acid soak process involves

5 contacting the coal with acid solution more than once. Preferably, the coal is contacted with the acid solution under the conditions of temperature and residence time outlined above. The coal and acid solution are then separated and the coal further contact with acid solution on one or more occasions. Figures 2 and 3 show schematic diagrams of some possible embodiments of the acid soak process 40.

10 After the acid soak process 40, the coal and acid solution are separated in separation unit 50. Separation unit 50 is suitably a filtration unit, especially a belt filter or a drum filter. The spent acid solution 52 is removed.

The recovered coal 54 is then subjected to a water wash 60. Water wash 60 is suitably achieved by spraying the filter cake of the belt filter or the drum filter with a wash water 62. The wash water is removed from the filter cake through the filtration unit, and the removed wash water is shown as reference numeral 64.

15 The washed filter cake 66, which comprises treated coal and a small amount of residual acid solution, is then passed to hydrothermal washing process 70. The washed coal 66 that is provided to hydrothermal washing process 70 has residual acid present in an amount such that when the washed coal 66 is reslurried in fresh water, the pH of the liquid phase will be approximately 2.

20 In hydrothermal washing process 70, water 72 and ethanol 74 are mixed with the coal. Preferably, the water and ethanol are mixed such that a solution of 50% ethanol in water is obtained. The amount of water, ethanol and coal fed to the hydrothermal washing process 70 is such that a slurry having a solids loading of 25% by weight is achieved. Suitably, the water, ethanol and coal are mixed prior to feeding to vessel 70.

25 In a most preferred embodiment of the present invention, the slurry in hydrothermal washing process 70 is heated to a temperature of 240 to 280° Celsius, especially 260 to 270° Celsius, by heating the slurry at a heating rate of between 2°

Celsius per minute and 20° Celsius per minute. Heating is conducted under autogenous pressure such that boiling is prevented. At the maximum temperatures reached in the hydrothermal washing process 70, the autogenous pressure is approximately 8 MPa. The slurry is suitably kept at the elevated temperature for a period of between 1 minute and 60 minutes, suitably 5 minutes. Under these conditions, the hydrothermal washing process reduces the level of sodium, silicon, iron and titanium in the coal, with the primary activity being reduction of sodium and silicon levels.

If only sodium is required to be reduced in hydrothermal washing process 70, the temperature used the hydrothermal wash stage can be as low as 10° Celsius and is suitably ambient temperature.

The slurry from hydrothermal washing process 70 is passed via line 76 to filtration unit 80. In filtration unit 80, the slurry from the hydrothermal washing process is separated into a coal fraction 82 and a liquid fraction 84. The liquid fraction 84 may be sent to an ethanol recovery unit 90, which is suitably a distillation column. In ethanol recovery unit 90, the liquid fraction 84 is split into a water rich fraction 92 and an ethanol rich fraction 94. Ethanol rich fraction 94 is suitably returned as stream 74 to the hydrothermal washing unit 70.

The coal fraction 82 is washed in washing process 100 using fresh wash water 102. The wash water is removed via stream 104 and a recovered ultra clean coal product 110 is recovered.

The ultra clean coal product is preferably subjected to a binderless briquetting process to produce a product having enhanced storage and transport properties.

The ultra clean coal product recovered from the process shown in figure 1 will typically have an ash content of between 0.01 and 0.2% by weight, with an ash fusion temperature sufficiently high to enable use of the ultra clean coal as a fuel for gas turbines. When the ultra clean coal is used to fire directly into gas turbines as part of a gas turbine combined-cycle power station, the ultra clean coal has the potential to reduce the greenhouse gas emissions by 25% when compared to modern coal fired thermal power stations. When the extra processing involved in obtaining the ultra clean coal is



taken into account, greenhouse gas emissions are still reduced by nearly 10% on an overall life-cycle basis.

As mentioned above, the acid soak process 40 may comprise a first slurrying of the coal with an acid solution, followed by re-slurrying of the coal between one and four times. Figure 2 shows one possible flow sheet for the acid soak process 40. In figure 2, the alkalised coal 36 is fed to a first acid soak vessel 140. An acid solution 142 is mixed with the alkalised coal 36 in vessel 140 for the desired time and under the desired temperature conditions. The acidified slurry of coal 144 then passes to a separator 146. The spent acid solution 148 is removed and the coal containing fraction 150 is thereafter fed to second acid soak vessel 152. Spent acid solution may be sent to caustic recovery step 24 for NaOH regeneration and recovery of minerals. Fresh acid solution 154 is mixed with the coal containing fraction in vessel 152 under the required conditions. The acidified slurry 156 is sent to second separator 158. The acid solution 160 is removed and the coal containing fraction 162 sent to either separation unit 50 as shown in figure 1 or, if further re-slurrying steps are required, sent to a further acid soak vessel 164. Broken lines 165 indicate that the sequence of soaking with fresh acid solution followed by separation may be repeated one or more times.

In vessel 164, the coal containing fraction 162 is mixed with fresh acid solution 166 for the desired time and under the desired conditions. The removed slurry 168 (which corresponds to slurry line 44 shown in figure 1) is then passed to separator 50 and water wash 60, which correspond to the respective separator 50 and water wash 60 of figure 1.

The re-slurrying of the coal with fresh acid solution preferably takes place between one and four times.

Figure 3 shows an alternative embodiment of the acid soak process in which a number of contacts are made between the acid solution and the coal fraction. In figure 3, the acid soak process is achieved by a multi-stage, counter current contacting between the coal and the acid solution. The process involves contacting the coal fraction with the acid solution in a number of contacting vessels 240, 242. The broken lines 244 indicate that there may be more contacting vessels than the two shown in figure 3. The coal 36 is fed to contacting vessel 240. The coal containing fraction 250 from vessel 240 is fed to

contacting vessel 242. The coal containing fraction 252 from contacting vessel 240 is then fed to either separation unit 50 (as shown in figure 1) or to one or more further contacting vessels (not shown).

Similarly, fresh acid solution 260 is fed to the downstream contacting vessel (242 in figure 3). The liquid fraction from 262 from vessel 242 is then fed to contacting vessel 240. The liquid fraction 264 from contacting vessel 260 is removed. The spent acid 264 may be sent to caustic regeneration (eg 24 in Figure 1) to regenerate an NaOH solution and recover precipitated minerals.

The process shown in figure 3 may utilise any apparatus known to be suitable to the man skilled in the art for counter current contact between solids and liquids. Such apparatus will be well known and need not be described further.

Figure 4 shows a flow sheet of a process in accordance with the second aspect of the present invention. For some uses, the coal product obtained from water wash 60 shown in figure 1 has sufficiently low ash content to be used without needing to undergo the hydrothermal washing process. Therefore, the process shown in figure 4 is essentially identical to that shown in figure 1, except that the coal fraction 66 from water wash 60 is not fed to the hydrothermal washing process, but rather goes to water wash 100, where it is washed with wash water 102 to obtain an ultra clean coal product 110. The ultra clean coal product 110 of figure 4 will have a somewhat higher ash content than the ultra clean coal product 110 of figure 1.

The remaining features of the process shown in figure 4 are essentially identical to those of figure 1 and the same reference numerals have been used in figure 4 for those features.

Figure 5 shows a flow sheet in accordance with the third aspect of the invention. In the flow sheet shown in figure 5, the coal 300 is subjected to a caustic digestion 302, and then to an acid wash or acid soak stage 304. The caustic digestion 302 and acid wash stage 304 of figure 5 may be the same or different to the respective stages described with reference to figure 1. The coal fraction 66' from acid soak 304 is fed to a hydrothermal washing process 70', followed by separation in filtration unit 80' into a liquid fraction 84'

and a coal containing fraction 82'. Liquid fraction 84' is fractionated into a water containing fraction 92' and a recovered ethanol fraction 94'.

Coal containing fraction 82' is washed in washing unit 100' and an ultra clean coal product 100' is recovered. The processing steps and conditions of hydrothermal washing process 70' shown in figure 5 is essentially identical to the hydrothermal washing process 70 with reference to figure 1.

Those skilled in the art will appreciate that the invention described herein may be subject to variations and modifications other than those specifically described. It is noted that the hydrothermal washing process may use an organic acid instead of the polar organic solvent, with citric acid being preferred. If citric acid is used in the hydrothermal washing process, the preferred conditions are as set out under the description of the first aspect of the present invention and the ethanol recovery process may be omitted.

The particular apparatus used in the present process includes any suitable apparatus known to the person skilled in the art. For example, the caustic digestion vessel 10 may comprise any suitable reactor including tubular concurrent-flow reactors, stirred autoclaves operating batch wise, or with continuous inflow and outflow, in single or multi stage configurations, or counter current or cross phase systems. As the apparatus that may be used in the process of the present invention will be well known to the person of skill in the art. It need not be described further.

It will be understood that the invention disclosed and defined herein extends to all alternative combinations of two or more of the individual features mentioned or evident from the text or drawings. All of these different combinations constitute various alternative aspects of the invention.

Dated this 1st day of November 2002

UCC Energy Pty Limited

by its attorneys

Freehills Carter Smith Beadle






FIGURE 1






FIGURE 4




FIGURE 5

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☒ OTHER: a lots dots

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**